

ESD-TR-67-493

ESD REPROD COPY

RETURN TO

SCIENTIFIC & TECHNICAL INFORMATION DIVISION
(ESTI), BUILDING 1211

ESD ACCESSION LIST

ESTI Call No. AI 57905Copy No. 1 of 1 cys

Technical Note

1967-33

Electroreflectance Study
of Interband
Magneto-Optical Transitions
in InAs and InSb at 1.5°K

C. R. Pidgeon
S. H. Groves
J. Feinleib

6 September 1967

Prepared under Electronic Systems Division Contract AF 19(628)-5167 by

Lincoln Laboratory

MASSACHUSETTS INSTITUTE OF TECHNOLOGY

Lexington, Massachusetts



A00658535

The work reported in this document was performed at Lincoln Laboratory, a center for research operated by Massachusetts Institute of Technology, with the support of the U.S. Air Force under Contract AF 19(628)-5167.

This report may be reproduced to satisfy needs of U.S. Government agencies.

This document has been approved for public release and sale; its distribution is unlimited.

MASSACHUSETTS INSTITUTE OF TECHNOLOGY
LINCOLN LABORATORY

ELECTROREFLECTANCE STUDY OF INTERBAND
MAGNETO-OPTICAL TRANSITIONS
IN InAs AND InSb AT 1.5°K

C. R. PIDGEON

National Magnet Laboratory, M.I.T.

S. H. GROVES

J. FEINLEIB

Group 84

TECHNICAL NOTE 1967-33

6 SEPTEMBER 1967

LEXINGTON

MASSACHUSETTS

ABSTRACT

The transparent electrode electroreflectance technique has been used for interband magneto-optical studies of InAs and InSb at 1.5°K. We report here the first direct experimental observation of the spin-orbit splitting ($\Delta = 0.38 \pm 0.01$ eV), the effective mass ($m_{\text{so}} = 0.14 \pm 0.01 m_0$) and the effective g-factor ($g_{\text{so}} = 13.0 \pm 1.0$) for the split-off band at $\vec{k} = 0$ in InAs.

Accepted for the Air Force
Franklin C. Hudson
Chief, Lincoln Laboratory Office

ELECTROREFLECTANCE STUDY OF INTERBAND
MAGNETO-OPTICAL TRANSITIONS
IN InAs AND InSb AT 1.5°K

Previous studies of magnetoelectroreflectance at room temperature,¹ using the electrolyte method of Cardona and co-workers,² have demonstrated the enhancement in sensitivity obtainable with electric field modulation of magneto-optical phenomena in semiconductors. The electrolyte method is suitable for work at temperatures above that of dry ice, and at wavelengths shorter than 2.5μ in the infrared. In the work discussed here a modification of the transparent electrode method of Seraphin and co-workers³ has been used to extend the measurements to liquid helium temperature and to wavelengths further into the infrared.⁴ We report here the first direct experimental observation of the spin-orbit splitting Δ , the effective mass m_{so} , and g-factor g_{so} of the split-off valence band at $\vec{k} = 0$ in InAs. Further experimental results are given for the direct valence and split-off valence to conduction band transitions in InSb. The latter results are similar to those reported by Aggarwal⁵ using the piezo-reflectance technique.

The transparent electrode technique as described in Ref. 3 uses a thin insulating spacer between the etched sample surface and a SnO_2 -glass electrode. The DC and AC electric fields are applied between the transparent electrode and sample, and the reflected light synchronously detected at the frequency of the AC electric field. Unless an optical matching material is used between the electrode and the insulator, there is a large unwanted wavelength dependent signal caused by interference of light reflected from the insulator/sample and electrode/insulator interfaces. This is modulated at the AC frequency by the mechanical vibration due to the electrical forces. Most optical matching fillers craze and become opaque when taken below 77°K. For this reason we have used a mechanically integrated thin film package, shown schematically in the lower insert of Fig. 1. The spacer layer, photo-resist material⁶ of thickness about 1μ , was spin coated onto the etched sample surface. A 65% transmitting Ni film (of surface resistance 1000 ohms per square) was deposited on this as




Fig. 1. Interband magneto-electroreflectance in InAs for $H = 84 \text{ kOe}$ at $T = 1.5^\circ \text{K}$. Inset shows the spectrum of the split-off valence to conduction band transitions for left and right circularly polarized light (σ_L and σ_R). The experimental arrangement of the electroreflectance package is also shown in the inset.

the transparent electrode. A thick gold tab was deposited at one end of the Ni, and a connecting foil or wire fastened to this with a conductive epoxy cement.⁷ With this arrangement it was possible to establish an electric field at the surface of the sample of $\sim 5 \times 10^5 \text{ V/cm}$. The magneto-electroreflectance was measured as described in Ref. 1, with the modification that the sample package was immersed in liquid helium and the experiments carried out at 1.5°K . PbS and cooled InAs and InSb detectors gave the required spectral sensitivity in the appropriate wavelength regions.

Figure 1 shows the magneto-electroreflectance spectrum for direct valence to conduction band transitions in InAs at $\vec{k} = 0$. In order to emphasize the magnetic effects, we have subtracted off the electroreflectance background, $\Delta R/R$,

obtained in this case in the absence of a magnetic field. An oscillatory spectrum is seen to much higher energies than in conventional techniques, and in particular the spin splitting of the first main line is easily resolved. The upper insert shows the magnetoelectroreflectance spectrum associated with the onset of split-off valence to conduction band transitions for left and right circularly polarized incident radiation (σ_L and σ_R). In this case the background electroreflectance was smaller and was not subtracted off. Good agreement was obtained between the spectrum for the low energy valence to conduction band transitions and the corresponding magneto-absorption data of Pidgeon, *et al.*,⁸ by associating the photon energies of the minima with the actual transition energies. This identification is maintained in higher energy regions where the spectra are not attainable by conventional magneto-absorption or reflection techniques.

In Fig. 2 are shown plots of the photon energy of the electroreflectance minima for the split-off valence to conduction band transitions as a function of magnetic field strength for the allowed transitions in the $\vec{E} \perp \vec{H}$ (σ_L and σ_R) spectrum. The solid lines give the transition energies calculated from effective mass theory^{9,10} using energy band parameters which retain a good fit to the magneto-absorption data of Ref. 8. The spin splitting of these transitions is clearly resolved, and a reasonable overall fit obtained, except in the case of the first spin split line where the difficulty of assigning a resonance position to a dispersion shape on a sharply rising background electroreflectance curve may account for the error. From the intercept on the ordinate at $H = 0$, after subtracting off the energy gap $E_g = 0.41$ eV (Ref. 8), we obtain an experimental value for the spin-orbit splitting at 1.5°K of $\Delta = (0.38 \pm 0.01)$ eV. This should be compared to a value of 0.43 eV obtained by Matossi and Stern,¹¹ from a theoretical fit to absorption edge measurements on p-type InAs. From the computed levels obtained by an overall best fit to the magneto-absorption spectra of Ref. 8 and the magnetoelectroreflectance data of Fig. 2 we obtain the following values for the band edge effective mass and g-value of the split-off band; $m_{so} = (0.14 \pm 0.01) m_0$ and $g_{so} = (13.0 \pm 1.0)$.




Fig. 2. Plot of the photon energy of magnetoelectroreflectance minima for the split-off valence to conduction band transitions in InAs as a function of magnetic field strength. The circles show the experimental points. The solid lines give the theoretical energies for the allowed transitions, fitted to the experimental data as discussed in the text.

Further results for the magnetoelectroreflectance of the direct transition in InSb at 1.5°K and 84 kOe are shown in Fig. 3. In this case a great deal more spectral fine structure is observed in the low energy region than in the case of InAs and, further, very little background electroreflectance is obtained in the absence of a magnetic field. It appears that both these results may be associated with the much greater purity of the InSb ($N \sim 1.0 \times 10^{14} \text{ cm}^{-3}$) than the InAs ($N \sim 2.0 \times 10^{16} \text{ cm}^{-3}$) samples used. The oscillatory spectrum again extends from the energy gap to very high energies, merging into the onset of split-off valence to conduction band transitions. The solid arrows show the




Fig. 3. Interband magnetoelectroreflectance in InSb for $H = 84 \text{ kOe}$ at $T = 1.5^\circ \text{K}$. Inset shows the spectrum of the split-off valence to conduction band transitions, with the solid arrows showing the theoretical energies for these transitions.

positions of these latter transitions calculated from the effective mass theory for coupled bands of Ref. 10. Good agreement both as to position and spin splitting of these lines is obtained which is consistent with the upper limit of the spin-orbit splitting obtained previously by Aggarwal⁵ using the piezo-reflectance technique ($\Delta = 0.81 \pm 0.01 \text{ eV}$).

It is expected from the theory of Elliott and Loudon¹² that the transitions observed in magneto-optical spectra should be excitonic. Experimental evidence for this in InSb has been given by Johnson¹³ from magneto-absorption studies. In fact, we observe very sharp symmetric lines both in the low energy magnetoelectroreflectance spectra of Fig. 3, and in the corresponding magneto-reflectance spectra. These line shapes seem characteristic of transitions to discrete exciton states, rather than the broader asymmetric lines one expects from transitions between Landau sub-bands where an integration over k_z is involved. There are two principal allowed ($\Delta n = 0, -2$) transitions in the first

set of lines between 0.250 and 0.260 eV. It appears that the first and third main lines are the exciton ground states associated with these, and that (in analogy with the work of Ref. 13) the higher energy shoulders may be associated with the first excited states. A further experimental and theoretical investigation of the detailed nature of the low energy spectral structure, and in particular of the additional unexplained strong lines near 0.256 eV and 0.275 eV will be the subject of another publication.

ACKNOWLEDGMENTS

The authors are grateful to K. Button, B. Lax and J. Mavroides for discussions and encouragement of this work. We thank B. Seraphin for advice concerning the transparent electrode technique, and T. Herndon for suggestions on the fabrication of the electoreflectance packages. We have also been helped by the work of R. Phelan on M.O.S. InSb detectors. J. Casteris and J. McNally have given experimental assistance, and M. J. Button and R. Morandi help with sample preparation.

REFERENCES

1. Groves, S.H., Pidgeon, C.R. and Feinleib, J., Phys. Rev. Letters 17, 643 (1966).
2. Cardona, M., Shaklee, K.L., and Pollak, F.H., Phys. Rev. 154, 696 (1967).
3. Seraphin, B.O. and Hess, R.B., Phys. Rev. Letters 14, 138 (1965); Seraphin, B.O., Phys. Rev. 140, A1716 (1965).
4. Pidgeon, C.R., Feinleib, J., Groves, S.H. and Phelan, R.J., Jr., Bull. Am. Phys. Soc. 12, 297 (1967).
5. Aggarwal, R.L., Bull. Am. Phys. Soc. 12, 100 (1967).
6. Kodak Photo-Resist, alternate layers of KTFR and KPR material were used.
7. Eccobond 57C, Emerson and Cuming, Inc., Canton, Massachusetts.
8. Pidgeon, C.R., Mitchell, and Brown, R.N., Phys. Rev. 154, 737 (1967).
9. Luttinger, J.M. and Kohn, W., Phys. Rev. 97, 869 (1955); Luttinger, J.M., Phys. Rev. 102, 1030 (1956).
10. Pidgeon, C.R. and Brown, R.N., Phys. Rev. 146, 575 (1966).
11. Matossi, F., and Stern, F., Phys. Rev. 111, 472 (1958).
12. Elliott, R.J. and Loudon, R., Phys. Chem. Solids 15, 196 (1960).
13. Johnson, E.J., Bull. Am. Phys. Soc. 12, 297 (1967).

DOCUMENT CONTROL DATA - R&D		
(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)		
1. ORIGINATING ACTIVITY (Corporate author) Lincoln Laboratory, M.I.T.		2a. REPORT SECURITY CLASSIFICATION Unclassified
		2b. GROUP None
3. REPORT TITLE Electroreflectance Study of Interband Magneto-Optical Transitions in InAs and InSb at 1.5°K		
4. DESCRIPTIVE NOTES (Type of report and inclusive dates) Technical Note		
5. AUTHOR(S) (Last name, first name, initial) Pidgeon, Carl R. Groves, Steven H. Feinleib, Julius		
6. REPORT DATE 6 September 1967	7a. TOTAL NO. OF PAGES 12	7b. NO. OF REFS 13
8a. CONTRACT OR GRANT NO. AF 19 (628)-5167	9a. ORIGINATOR'S REPORT NUMBER(S) Technical Note 1967-33	
b. PROJECT NO. 649 L		
c.		
d.	9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report) ESD-TR-67-493	
10. AVAILABILITY/LIMITATION NOTICES This document has been approved for public release and sale; its distribution is unlimited.		
11. SUPPLEMENTARY NOTES None	12. SPONSORING MILITARY ACTIVITY Air Force Systems Command, USAF	
13. ABSTRACT <p>The transparent electrode electroreflectance technique has been used for interband magneto-optical studies of InAs and InSb at 1.5°K. We report here the first direct experimental observation of the spin-orbit splitting ($\Delta = 0.38 \pm 0.01$ eV), the effective mass ($m_{SO} = 0.14 \pm 0.01 m_0$) and the effective g-factor ($g_{SO} = 13.0 \pm 1.0$) for the split-off band at $k = 0$ in InAs.</p>		
14. KEY WORDS magnetoelectroreflectance indium arsenide magneto-optical transitions indium antimonide semiconductors		